



Technical Data Sheet

FSC Flexible Silicone Coating

Product Description

FSC is fast drying and is designed to protect printed circuit boards, particularly those exposed to high humidity environments. Based on a high quality silicone resin, FSC exhibits excellent adhesion to a wide variety of substrates and operates within a wide temperature range.

Features

- Fluoresces under UV light for ease of inspection.
- Wide operating temperature range and resistant to mould growth.
- Can be soldered through without fear of highly toxic gases being produced (contains no isocyanates).
- Non-corrosive to Cadmium and Zinc plate (contains no phenols).
- Cured coating can be removed with Electrolube Ultrasolve (ULS).
- Excellent Dielectric properties

Approvals

**RoHS Compliant (2002/95/EC):
IEC 61086-2**

**Yes
Approved**

Liquid Properties

Appearance:	Clear translucent liquid
Specific Gravity (Density) @ 20°C:	1.05 (Bulk) g/ml
VOC Content:	50% (Bulk)
Solids content:	50% (Bulk)
Viscosity @ 20°C:	550 Centipoise (Bulk)
Touch Dry:	10-15 minutes
Recommended Drying Time:	24 Hours @ 20°C 4 Hours @ 60°C 2 Hours @ 90°C
Coverage @ 25µm:	15m ² per litre (Bulk)

Dry Film Coating

Colour:	Colourless
Operating Temperature Range:	-50°C to +125°C
Flammability:	Self-extinguishing
Thermal Cycling (IEC 60086-2-14):	Pass
Coefficient of Expansion:	150ppm
Dielectric Strength:	80 kV/mm
Dielectric Constant:	2.7
Insulation Resistance:	1 x 10 ²⁰ Ohms/cm
Dissipation Factor @ 100Hz @ 25°C	0.001
Moisture Resistance (IEC 60058-2-78):	Pass
Salt Spray (IEC 60086-2-14)	Pass

<u>Packaging</u>	<u>Description</u>	<u>Order Code</u>	<u>Shelf Life</u>
<u>FSC Conformal Coating</u>	400ml Aerosol	FSC400	24 Months
	5 Litre Bulk	FSC05L	36 Months
<u>Non-Acrylic Thinners</u>	1 Litre	DCT01L	36 Months
	5 Litre	DCT05L	36 Months
<u>Removal Solvent</u>	200ml Aerosol	ULS200D	36 Months
	400ml Aerosol	ULS400D	36 Months
	1 Litre Bulk	ULS01L	72 Months
	5 Litre Bulk	ULS05L	72 Months
	25 Litre Bulk	ULS25L	72 Months

Directions For Use

FSC can be sprayed, dipped or brushed. The thickness of the coating depends on the method of application (typically 25 microns). Temperatures of less than 16°C or relative humidity in excess of 75% are unsuitable for the application of FSC. As is the case for all solvent based conformal coatings, adequate extraction should be used (refer to MSDS for further information).

Substrates should be thoroughly cleaned before coating. This is required to ensure that satisfactory adhesion to the substrate is achieved. Also, all flux residues must be removed as they may become corrosive if left on the PCB. Electrolube manufacture a range of cleaning products using both hydrocarbon solvent and aqueous technology. Electrolube cleaning products produce results within Military specification.

Spraying – Bulk

FSC needs to be diluted with the appropriate thinners (DCT) before spraying. The optimum viscosity to give coating quality and thickness depends on the spray equipment and conditions, but normally a suitable spray viscosity is typically 50-80 centipoise. If bulk coating material has been agitated, allow to stand until air bubbles have dispersed.

FSC is suitable both for use in manual spray guns and selective coating equipment.

The selected nozzle should enable a suitable even spray to be applied in addition to suiting the prevailing viscosity. The normal spray gun pressure required is 274 to 413 kPa (40 - 60 lbs/sq.inch). After spraying, the boards should be placed in an air-circulating drying cabinet and left to dry.

Spraying - Aerosol

When applying FSC in aerosol form care must be taken to ensure the can is not shaken before use. Shaking the can will introduce excessive air bubbles and will give a poor coating finish.

The can should be held at 45°, and 200mm from the substrate to be coated. The valve should then be depressed when the can is pointing slightly off target and moved at about 100mm / second across the target. To ensure the best coating results are achieved try to use a smooth sweeping motion with small overlap for successive rows.

To ensure penetration of the coating beneath the components and in confined spaces, spray the assembly from all directions to give an even coating. After spraying, the boards should be placed in an air-circulating drying cabinet and left to dry.

Dip Coating

Ensure that the coating material in the container has been agitated thoroughly and has been allowed to stand for at least 2 hours for all the air bubbles to disperse.

Non acrylic conformal coating thinners (DCT) should be used to keep the FSC coating at a suitable viscosity for dipping. DCT is added periodically as the solvent evaporates. The viscosity should be checked using a viscosity meter or "flow cup".

The board assemblies should be immersed in the FSC dipping tank in the vertical position, or at an angle as close to the vertical as possible. Connectors should not be immersed in the liquid unless they are very carefully masked. Electrolube Peelable Coating Mask (PCM) is ideal for this application.

Leave submerged for approximately 10 seconds until the air bubbles have dispersed. The board or boards should then be withdrawn slowly (1 to 2 Seconds / mm) so that an even film covers the surface. After withdrawing, the boards should be left to drain over the tank or drip tray until the majority of residual coating has left the surface.

After the draining operation is complete, the boards should be placed in an air-circulating drying cabinet and left to dry.

Brushing

Ensure that the coating material has been agitated thoroughly and has been allowed to settle for at least 2 hours. The coating should be kept at ambient temperature.

When the brushing operation is complete the boards should be placed in an air-circulating drying cabinet and left to dry.

Inspection

FSC contains a UV trace, which allows inspection of the PCB after coating to ensure complete and even coverage. The stronger the reflected UV light, the thicker the coating layer is.

Revision 1 (February 2008)

Copyright Electrolube 2007

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.