



# TECHNICAL DATA SHEET

CATEGORY: **NO-CLEAN CORED WIRE SOLDER**  
NAME: **GLOW CORE**

## FEATURES

- EXCELLENT WETTING
- LEAD-FREE COMPATIBLE
- WIDE PROCESS WINDOW
- CLEANABLE WITH SAPONIFIER

## DESCRIPTION

**GLOW CORE** is a no-clean, resin-based flux cored wire solder designed to offer excellent wetting characteristics and lead-free compatibility. This product is very active and is recommended for fast cycle time soldering. **GLOW CORE** flux promotes good thermal transfer, offering better solder penetration into plated through holes or surface mount interconnections. **GLOW CORE** cored wire produces low-to-medium post-process residues that are electrically safe and do not require cleaning for most applications.

## HANDLING

- **GLOW CORE** cored wire has an indefinite shelf life when proper storage conditions are observed.
- Store **GLOW CORE** in a clean, dry area away from moisture and sunlight. Do not freeze this product

## APPLICATION

- Solder iron tip temperature should be between 650° - 750°F (350° - 400°C) for Sn63, Sn62 and Sn60 alloys, 700° - 800°F (370° - 425°C) for Sn/Ag and Sn/Ag/Cu (SAC305, CASTIN, TSC-4, etc.) alloys.
- Hold the solder iron tip at a 45° to 60° angle to the work surface.
- The solder iron should contact both the component lead and PCB pad surface.
- Solder and flux should flow onto the lead and pad or lead and barrel to promote optimum flux activity for the joint being worked.
- If additional flux is needed, the use of AIM flux dispensing pens is recommended for dispensing precise amounts of flux to eliminate over-saturation.

## CLEANING

**GLOW CORE** can be cleaned with saponified tap water or an alcohol and water blend. **AIMTERGE 520** is recommended. A water temperature of 140°F is recommended, and should be adequate for removing any post-process residues.

## PACKAGING

- **GLOW CORE** is standard with a 2.5% flux core.
- **GLOW CORE** is available in Sn/Ag/Cu, CASTIN, SN100C, and other alloys upon request.
- Standard spool sizes: ½ lb. for .010 and .015 diameters, and 1lb. for .020, .032, .040, .050 and .062 diameters. Other diameters and spool sizes are available upon special request.
- Packaging of ½ lb. and 1 lb. spools is available in 12 lb. and 24 lb. cases.

## SAFETY

- Use with adequate ventilation and proper personal protective equipment.
- Refer to the accompanying **Material Safety Data Sheet** for any specific emergency information.
- Do not dispose of any hazardous materials in non-approved containers.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please review AIM's terms and conditions at [www.aimsolder.com/t&c.cfm](http://www.aimsolder.com/t&c.cfm)

07.29.05

Manufacturing and Distribution Worldwide

Americas +1-401-463-5605 • Europe +44-1737-222-258 • Asia-Pacific +852-2649-7183 • [info@aimsolder.com](mailto:info@aimsolder.com) • [www.aimsolder.com](http://www.aimsolder.com)



# PRODUCT TESTING RESULTS

CATEGORY: **CORED WIRE MEDIUM**  
 NAME: **GLOW CORE**

## Surface Insulation Resistance

Surface Insulation Resistance (SIR) test for cored wire flux was carried out according to J-STD-004 and IPC-TM-650 method 2.6.3.3.

### Pass-Fail Criteria and Data Evaluation

Reference	Property	Pass-Fail Criteria	Result
IPC-TM-650 method 2.6.3.3. §5.5.1	Control coupons	>1E9 Ω at 96 and 168 h	<b>PASS</b>
J-STD-004 §3.2.4.5.1	Sample coupons	>1E8 Ω at 96 and 168 h	<b>PASS</b>
IPC-TM-650 method 2.6.3.3. §5.5.2	Post-test visual inspection	No dendrite growth or corrosion	<b>PASS</b>

### Conclusions

The result of the qualification test indicates that GLOW CORE wire solder complies with the requirements of IPC TM-650, Method 2.6.3.3 for Surface Insulation Resistance.

### Test Data

Control		Initial	24 hours	96 hours	168 hours
#1	A	5.03E+13	8.03E+09	9.73E+09	8.78E+09
	B	5.03E+13	8.32E+09	9.92E+09	9.72E+09
	C	3.35E+13	9.21E+09	1.03E+10	1.02E+10
	D	3.35E+13	8.67E+09	1.13E+10	9.72E+09
#2	A	2.01E+13	8.23E+09	9.73E+09	9.06E+09
	B	2.51E+13	7.76E+09	9.51E+09	9.36E+09
	C	2.01E+13	8.87E+09	1.01E+10	9.67E+09
	D	2.51E+13	7.98E+09	1.05E+10	9.04E+09
#3	A	1.00E+14	1.48E+10	1.65E+10	1.62E+10
	B	3.35E+13	1.46E+10	1.71E+10	1.70E+10
	C	1.00E+14	1.45E+10	1.64E+10	1.62E+10
	D	5.03E+13	1.36E+10	1.70E+10	1.58E+10
<b>FastCore wire</b>					
#1	A	1.00E+14	9.99E+08	1.47E+09	1.28E+09
	B	1.10E+14	1.09E+09	6.17E+08	5.19E+08
	C	1.00E+14	1.77E+09	2.17E+09	1.68E+09
	D	1.00E+14	1.09E+09	1.65E+09	1.31E+09
#2	A	1.10E+14	5.87E+08	2.90E+08	1.84E+08
	B	1.10E+14	1.53E+09	1.14E+09	1.01E+09
	C	1.00E+14	7.08E+08	8.46E+08	7.43E+08
	D	1.10E+14	4.55E+08	5.74E+08	5.88E+08
#3	A	1.00E+14	7.49E+08	3.46E+08	2.46E+08
	B	8.01E+13	9.03E+08	1.08E+09	9.24E+08
	C	1.10E+14	6.95E+08	6.42E+08	4.96E+08
	D	1.67E+13	7.72E+08	8.93E+08	7.36E+08

Manufacturing and Distribution Worldwide

Americas +1-401-463-5605 • Europe +44-1737-222-258 • Asia-Pacific +852-2649-7183 • info@aimsolder.com • www.aimsolder.com